

WAX TEST INFO #2



Place: Östersund
Date : 05.01.2018

Testers: EE.UE

Glide

Test time: 15,00 to 15,45

Rank	Ski#	Glidewax / Powder / Top Coat	Feeling
1.		HF Röd/JSP Röd/HeiX Röd	
2.		HF Röd/JSP Röd	
3.		HF Röd/JSP Blå	
4.		HF Röd	

Structure

Very fine Fine Medium Coarse

Kick

Test time: to 15,00 to 15,45

Rank	Ski#	Wax	Wax	Kick	Feeling
1		Grön Base	Röd	1	1
2		Grön Base	Blå	2	2

Snow and weather info

Measurement time: 15,00

Snow temperature (°C): -5,1
Air temperature (°C): -7,0
Snow humidity (ref. Doser instr.): 18
Air humidity (% rH): 78%

Clouds (sky parts covered):
Visibility:
Wind:
Precipitation:

ARTIFICIAL SNOW	NATURAL SNOW	GRAIN SIZE	SNOW HUMIDITY	TRACK HARDNESS	TRACK CONSISTENCE
o A1 Falling new o A2 New o A3 Irreg. dir. new o A4 Irreg. dir. transf. o A5 Transformed	o FN Falling new o NS New o IN Irreg. dir. new o IT Irreg. dir. transf. o TR Transformed	o G0 0.0 - 0.2 mm. Extra fine o G1 0.2 - 0.5 mm. Very fine o G2 0.5 - 1.0 mm. Fine o G3 1.0 - 2.0 mm. Average o G4 2.0 - 4.0 mm. Coarse o G5 > 4.0 mm. Very coarse	o DS Dry o W1 Moist o W2 Wet o W3 Very wet o W4 Slush	o H1 Very soft o H2 Soft o H3 Med. hard o H4 Hard o H5 Very hard o H6 Ice	o T1 Partly shiny o T2 Shiny o D1 Partly dirty o D2 Dirty

Niclas Jacobsson
niclas@swixsport.se